



## Davis Colors™ Red 10134

Beltville • MD • 1-301-210-3400 • Los Angeles • CA • 1-323-269-7311 • Matlock • UK  
 +44 (0) 1629 582 245 • Walluf • Germany • +49 (0) 6123 797-0 • Torino • Italy • +39 011  
 2280501 • Singapore • +65 532 0676 • Shanghai • China • +86 21 5298 6368  
 www.rockwoodpigments.com • info@rpigments.com

Pigment Red 101 • Color Index No. 77491 • CAS 1309-37-1

### Davis Colors™ Synthetic Iron Oxide Red 10134

Description

Davis Colors™ Red 10134 is a blend of Light-shade primary synthetic iron oxide reds (Fe<sub>2</sub>O<sub>3</sub>). It is designed for use in concrete, concrete products and mortar. It is manufactured in large batches on intensive grinding and blending equipment. Each batch is measured throughout the process and verified on spectrophotometer to certify its conformance with standards for tint strength and shade. It meets or exceeds ASTM C979-82 standards for pigments used in cement. Davis Colors™ 10134 is color-stable in processing temperatures below 1000°C (1832°F). It is of sufficient purity for use in packaging or articles that come in contact with food (21CFR), but not suitable for the direct coloration of pet food or cosmetics. All Davis Colors™ iron oxides are manufactured under strict QC and environmental controls for reliable and consistent quality, stable under exposure to sunlight and UV radiation and are alkali, chemical and weather resistant. Davis Colors™ Red 10134 is packaged in 50 pound multiwall paper bags and shrink-wrapped onto pallets of 2000 pounds and also available in Mix-Ready® disintegrating bags. *Uses: concrete, masonry, pavers, roof tile, brick, stone, stucco, plaster, low-gloss paint, plastics and rubber.*

Composition/Typical Properties

Fe <sub>2</sub> O <sub>3</sub> content (%)	95 – 96
SiO <sub>2</sub> content (%)	<1
Oil Absorption (g/100g)	24
Weight per Gallon (lbs)	40
Specific Gravity (g/cm <sup>3</sup> )	4.8
Bulk Density (lbs/ft <sup>3</sup> )	25
325 Mesh Retention (%)	<0.2
Water Soluble Salts (%)	<0.5
Ignition Loss (%)	<2
Moisture content (%)	<1
pH	3 – 7
Particle Shape	Spherical
Predominant Particle Size (µm)	0.27

Typical Trace Metal Content in Parts Per Million (ppm)

Arsenic (As)	<10
Antimony (Sb)	<15
Cadmium (Cd)	<1
Chromium (III) (Cr)	<350
Copper (Cu)	<300
Lead (Pb)	<5
Mercury (Hg)	<1
Nickel (Ni)	<50
Selenium (Se)	<2

*The values for typical contents and trace metals are provided as general information only. They are approximate values for reference and not specifications utilized in our standard QC procedures for color and consistency.*

This product information is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best knowledge of Rockwood Pigments, Inc. or obtained from sources we believe are accurate. We disclaim any legal responsibility for use or reliance on this information and expressly disclaim that use of this product, either alone or in combination with other materials, will not violate the claims of any patent or rightful claim of any third party. Since you are in control of the application, process and conditions of use of our products, you have an obligation to test the products supplied by us to determine their suitability for the intended processes and uses. Despite this, if liability should be established for any damage, buyer's sole remedy shall be refund of product purchase price from point of purchase. We will, of course, provide consistent quality of our products within the scope of our General Conditions of Sale and Delivery. Before using any chemical, read its label and Material Safety Data Sheet.